

Dimensionering af FireProtect til standardprofiler - 120 min.

HE A-profil - brandklasse 120 min.						
Isoleret	4-sidet			3 sidet		
T-krit °C	450	500	550	450	500	550
Profilnr.						
100	-	-	100	100	80	80
120	-	-	100	100	80	80
140	-	100	100	80	80	60
160	100	100	100	80	80	60
180	100	100	80	80	80	60
200	100	80	80	80	60	50
220	100	80	80	60	50	50
240	80	80	60	60	50	50
260	80	80	60	60	50	40
280	80	80	60	60	50	40
300	80	60	50	50	40	30
320	60	50	50	50	40	30
340	60	50	50	50	40	30
360	60	50	50	40	30	25
400	60	50	40	40	30	25
450	60	50	40	40	30	25
500	60	40	30	40	30	25
550	50	40	30	40	30	25
600	50	40	30	40	30	25
650	50	40	30	40	30	25
700	50	40	30	40	30	25
800	50	40	30	40	30	25
900	50	40	30	40	30	25
1000	50	40	30	40	30	25

HE B-profil - brandklasse 120 min.						
Isoleret	4-sidet			3 sidet		
T-krit °C	450	500	550	450	500	550
Profilnr.						
100	100	80	80	80	80	60
120	100	80	80	80	60	60
140	80	80	60	60	60	50
160	80	80	60	60	50	40
180	80	60	50	60	50	40
200	80	60	50	50	40	30
220	60	50	50	50	40	30
240	60	50	50	40	30	25
260	60	50	40	40	30	25
280	60	50	40	40	30	25
300	60	50	40	30	25	20
320	50	40	30	30	25	20
340	50	40	30	30	25	20
360	50	40	30	30	25	20
400	50	40	30	30	25	20
450	40	30	25	30	25	20
500	40	30	25	30	25	20
550	40	30	25	30	25	20
600	40	30	25	30	25	20
650	40	30	25	30	25	20
700	40	30	25	30	25	20
800	40	30	25	30	25	20
900	40	30	25	30	25	20
1000	40	30	25	30	25	20

HE M-profil - brandklasse 120 min.						
Isoleret	4-sidet			3 sidet		
T-krit °C	450	500	550	450	500	550
Profilnr.						
100	-	100	100	100	80	80
120	100	100	80	80	80	60
140	100	80	80	80	60	50
160	80	80	60	60	50	50
180	80	80	60	60	50	40
200	80	60	50	60	50	30
220	80	60	50	50	40	30
240	60	50	50	50	40	30
260	60	50	50	50	40	30
280	60	50	50	40	30	25
300	60	50	50	40	30	25
320	60	50	40	40	30	25
340	60	50	40	40	30	25
360	50	40	30	40	30	25
400	50	40	30	30	25	20
450	50	40	30	30	25	20
500	40	30	25	30	25	20
550	40	30	25	30	25	20
600	40	30	25	30	25	20
650	40	30	25	30	25	20
700	40	30	25	30	25	20
800	40	30	25	30	25	20
900	40	30	25	30	25	20
1000	40	30	25	30	25	20

Dimensionering af FireProtect til standardprofiler - 120 min.

IPE-profil - brandklasse 120 min.

Isoleret	4-sidet			3 sidet		
T-krit °C	450	500	550	450	500	550
Profilnr.						
80	-	-	-	-	-	-
100	-	-	-	-	-	-
120	-	-	-	-	-	-
140	-	-	-	-	-	-
160	-	-	-	-	-	100
180	-	-	-	-	-	100
200	-	-	-	-	100	100
220	-	-	100	100	100	100
240	-	-	100	100	100	80
270	-	100	100	100	80	80
300	100	100	100	100	80	80
330	100	100	80	100	80	80
360	100	80	80	80	80	60
400	100	80	80	80	80	60
450	80	80	60	80	60	60
500	80	80	60	80	60	60
550	80	80	60	60	50	50
600	80	60	60	60	50	50

INP-profil - brandklasse 120 min.

Isoleret	4-sidet			3 sidet		
T-krit °C	450	500	550	450	500	550
Profilnr.						
80	-	-	-	-	-	-
100	-	-	-	-	-	-
120	-	-	-	-	-	-
140	-	-	-	-	-	100
160	-	-	-	-	100	100
180	-	-	100	100	100	80
200	-	100	100	100	80	80
220	100	100	100	100	80	80
240	100	80	80	80	80	60
260	100	80	80	80	80	60
280	100	80	80	80	80	60
300	80	80	60	80	60	50
320	80	80	60	60	50	50
340	80	60	50	60	50	50
360	80	60	50	60	50	40
380	60	50	50	60	50	40
400	60	50	50	60	50	40
425	60	50	40	50	40	30
450	60	50	40	50	40	30
475	50	40	40	40	30	30
500	50	40	30	40	30	30
550	50	40	30	40	30	25
600	40	30	25	40	30	20

UNP-profil - brandklasse 120 min.

Isoleret	4-sidet			3 sidet		
T-krit °C	450	500	550	450	500	550
Profilnr.						
80	-	-	-	-	-	-
100	-	-	-	-	-	-
120	-	-	-	-	100	100
140	-	-	100	-	100	100
160	-	-	100	-	100	80
180	-	100	100	100	100	80
200	-	100	100	100	80	80
220	100	100	80	100	80	80
240	100	100	80	100	80	80
260	100	80	80	80	80	60
280	100	80	80	80	80	60
300	100	80	80	80	80	60
320	80	80	60	80	80	60
350	80	80	60	80	80	60
380	80	80	60	80	60	50
400	80	80	60	80	50	50

Dimensionering af FireProtect til standardprofiler - 120 min.

UPE-profil - brandklasse 120 min.						
Isoleret	4-sidet			3 sidet		
T-krit °C	450	500	550	450	500	550
Profilnr.						
80	-	-	-	-	-	-
100	-	-	-	-	-	-
120	-	-	-	-	-	100
140	-	-	-	-	-	100
160	-	-	-	-	100	100
180	-	-	-	-	100	100
200	-	-	100	100	100	100
220	-	100	100	100	100	80
240	-	100	100	100	80	80
260	100	100	100	100	80	80
280	100	80	80	80	80	60
300	80	80	60	80	80	60
320	80	80	60	80	60	50
340	80	80	60	60	50	50