






	PRODUKT	FASE A1-A3 (Produktion)	FASE A1-A3, A4 (Produktion+Transport)	LCA IHT. BR18 (A1-A3, C3, C4)
	<b>GNE 13</b>	1,570	1,658	2,216
	<b>GNE13 Klima</b>	<b>-0,047</b>	<b>0,285</b>	<b>0,653</b>
	<b>GEE 13</b>	1,130	1,250	1,777
	<b>GEE 13 Klima</b>	<b>-0,019</b>	<b>0,230</b>	<b>0,657</b>
	<b>GRE 13</b>	2,090	2,298	2,933
	<b>GRE 13 Klima</b>	<b>-0,154</b>	<b>0,276</b>	<b>0,748</b>
	<b>GRIE 13</b>	3,00	3,059	3,160
	<b>GRIE 13 Klima</b>	<b>0,065</b>	<b>0,512</b>	<b>1,024</b>
	<b>GU 9</b>	1,140	1,210	1,820
	<b>GU 9 Klima</b>	<b>0,221</b>	<b>0,354</b>	<b>0,934</b>
	<b>GFE 15</b>	2,570	2,796	3,230
	<b>GFE 15 Klima</b>	<b>0,222</b>	<b>0,692</b>	<b>0,957</b>

Sammenligning af CO<sub>2</sub>-aftryk for Gyproc gipsplader (kg CO<sub>2</sub> eq./m<sup>2</sup>)